

FISHER CAT FIBER Co.

by ANNIE CADDEN

Goldenrod

Solidgo

4 ounces scoured wool
10-12 ounces goldenrod plant tops
Stainless steel stockpot
1 1/2 tsp alum* (aluminum sulphate)*
1 1/2 tsp cream of tartar

Presoak wool in warm tap water.
Place blossoms in the pot covered with water.
Simmer for 1-2 hours, remove blossoms.
Dissolve alum & cream of tartar in hot water and stir into dye liquid.
Stir evenly until dissolved in dye bath.
Add wool, heat on medium heat (160-180°F) for 1 hour.
Remove wool from dye pot, rinse in warm water until liquid runs clear.
Hang in shade to dry.

Safety Tips: Never use everyday kitchen equipment. Keep dye pots and equipment separate. Wear heat resistant gloves, especially when handling mordants*. Dye outdoors or in well ventilated area.

New to Natural Dyeing? We recommend [Botanical Colors](#) for instruction on how to scour and mordant your wool and for purchasing supplies and mordants.

Questions? Email us at hello@fishercatfiberco.com

